

Asylum segments "Consul 50"

Purpose:

- separation of lanes
- Securing off-street areas, junctions and pedestrian crossings
- Separation of cycle lanes
- chicanes before entering towns

Place of production:

Poland

Material:

SBR rubber granulate PUR resin Metal reinforcement for assembly Reflective element - micro beads Optional 3M white reflective tape



Dimensions:

| Item name | Length (mm) | Width (mm) | Height (mm) | Weight (kg) |
|-----------|-------------|------------|-------------|-------------|
| 1. ZAN 50 | 500 | 500 | 100 | 20,0 |
| 2. ZAS 50 | 500 | 500 | 100 | 22,0 |
| 3. ZAW 50 | 500 | 500 | 100 | 23,5 |

Option available to order a personalised solution according to customer design.

Colour:

Red/grey

Edging painted with glass microspheres

Technical parameters:

| Parameters | Value | Unit | Standard / Method |
|---------------------------|-------|------|--------------------|
| Tensile strength | ≥ 1,0 | MPa | PN-ISO 37 |
| Hardness | ≥ 55 | °ShA | PN-EN ISO 868:2005 |
| Water absorption | ≤ 2 | % | PN-EN ISO 62 |
| Tolerance - length, width | ± 2 | % | of nominal |
| Tolerance - height | ± 2 | % | of nominal |
| Tolerance- weight | ± 2 | % | of nominal |

TRAFFICMINDS Kft. | Magyarország 2094 Nagykovácsi, Táncsics köz 9.


TIN: 14580835-2-13 | CRN: 13 09 192833


Tel: + 36 30 631 4193

E-mail: trafficminds@trafficminds.hu www.trafficminds.hu



Technical drawings:





Packing:

Packed on a Euro pallet. Protected by protective film and strapped with tape.

Description on the pallet with the name of the product, its quantity, batch number and packing date. On customer's request other way of packing possible

Identification:

Product- on the underside of the product information about the date of production.

Pallet- product name, quantity, pallet identification number, packing date, quality control stamp.

Storage:

The products should be stored on pallets in protective film and protected from external weather conditions.

The products may be stored for a longer period of time only in closed, ventilated rooms without humidity, after removing the protective film. Storage temperature: max 40 oC

Health, safety and fire conditions:

Conditions for storage and use of the product- must meet all requirements for storage and use of rubber materials.